

STELLITE® 3 ALLOY

TECHNICAL DATA

Nominal Composition (mass %) and Physical Properties

Co	Cr	W	C	Others	Hardness	Density	Melting Range
Base	30.5	12.5	2.3	Ni, Fe, Si,	48-63 HRC	8.64 g/cm ³ 0.312lb/in ³	2215-2345°F 1213-1285 °C

Stellite® cobalt base alloys consist of complex carbides in an alloy matrix. They are resistant to wear, galling and corrosion and retain these properties at high temperatures. Their exceptional wear resistance is due mainly to the unique inherent characteristics of the hard carbide phase dispersed in a CoCr alloy matrix.

Description

The high carbon content of this alloy increases the volume fraction of carbides and hence its abrasion and solid particle erosion resistance. The high tungsten content improved its high temperature properties. However, this results in material which is nearly impossible to hardface crack free and one that withstands almost no impact. It has excellent metal-to-metal wear resistance and resists galling when mated with other Stellite® Alloys

Corrosion Resistance

This alloy is considered inferior to Stellite® alloys 6 and 12 in most environments. Like all Stellite® alloys, it has excellent resistance to oxidation but is not recommended for reducing acids. Stellite® alloy 3 is resistant to nitric acid over a range of concentrations at room temperature. It also has excellent resistance to phosphoric acid below 150°F and formic acid at room temperature. It also is highly resistant to sulphuric acid but only at room temperature. Since corrosion resistance varies with concentration, temperature, stress and contaminants, it is best to use production exposure tests to determine the suitability for each application.

Wear

The higher carbon content results in an increase in volume fraction of carbides and higher abrasion resistance in low stress abrasion tests. Stellite® alloy 3 is 3 to 4 times more resistant than Stellite® alloy 6 and twice as resistant as Stellite® alloy 12. It is also superior to Delcrome® 90 and 07 tool steel. In metal on metal wear Stellite 3 is superior and this improved resistance increases as loads are increased or speeds are increased to 10 times to 25 times that of Stellite® alloy 6 or 12. This alloy also has higher hot hardness and resists galling like all Stellite® alloys when mated with another Stellite® alloy. The material is also resistant to erosion and most combinations of heat and wear.

Finishing

This alloy is more difficult to machine than Stellite® alloy 6, but can be turned with carbide tip tools. If the hardness exceeds RC55 grinding is the preferred method. The material should be stress relieved before and during machining.

Nominal Thermal Expansion Coefficient (from 20°C/68°F to stated temperature)

	100°C (212°F)	200°C (392°F)	300°C (572°F)	400°C (752°F)	500°C (932°F)	600°C (1112°F)	700°C (1292°F)	800°C (1472°F)	900°C (1652°F)	1000°C (1832°F)
μ-inch/inch.°F	5.83	6.28	6.56	6.72	6.94	7.11	7.5	7.72	8.0	8.2

Nominal Tensile Properties at Room Temperature

	Ultimate Tensile Strength Rm		Yield Stress Rp(0.2%)		Elongation	Elastic Modulus	
	ksi	MPa	ksi	MPa	A(%)	ksi	MPa
Castings	80	551	-	-	<1	34,100	235x10 ³

Nominal Hot Hardness (DPH) as-cast

20°C (68°F)	100°C (212°F)	200°C (392°F)	300°C (572°F)	400°C (752°F)	500°C (932°F)	600°C (1112°F)	700°C (1292°F)	800°C (1472°F)	900°C (1652°F)
606	573	540	508	485	453	406	330	217	140

Thermal and Electrical Properties

	Approximate value at Room Temperature
Thermal conductivity	102 Btu-in/hr/ft ² /°F
Electrical resistivity	269.24 μ-ohm.inch

Applications

Recommend for use as surgical scissor inserts, valve seat inserts, needle holders, steel mill guide rolls, seaming rolls, sleeves, bushings, bearing balls, wear pads, burner nozzles and palm guides.

Available forms

Welding powder or rod; cast components; powder metallurgy components.

Specifications

USN R30001; AWS A5.13 RCoCr-C; MIL-R-17131; RCoCr-C; SAE J775; MIL-C-15345 Alloy 22; MIL-C-24248 Comp IV

Stellite is a registered Trade Name of Deloro Stellite.

Deloro Stellite manufactures sophisticated alloys in the form of castings, powders, coatings, consumables, and machined parts that resist wear, corrosion, and abrasion. Information provided in this document is intended only for general guidance about Deloro Stellite products and is the best information in our possession at the time. Product users may request information about their individual use of our products, but Deloro Stellite does not warrant or guarantee this information in any way. Selection and purchase of Deloro Stellite products is the sole responsibility of the product user based on the suitability of each use. Individual applications must be fully evaluated by the user, including compliance with applicable laws, regulations, and non-infringement. Deloro Stellite cannot know or anticipate the many variables that affect individual product use and individual performance results may vary. For these reasons, Deloro Stellite does not warrant or guarantee advice or information in this document, assumes no liability regarding the same, and expressly disclaims any warranty of any kind, including any warranty of fitness for a particular purpose, regarding the same.



UK SALES OFFICE

Deloro Stellite
Cheney Manor Industrial Estate
Swindon SN2 2PW
UK

Tel: (+44) 1793-498500
Fax: (+44) 1793-498501

E-Mail: saleshad@stellite.com

Literature Number:461-3
Copyright © 2008 Deloro Stellite
Printed in USA

www.stellite.com

US SALES OFFICE

Stellite Coatings
1201 Eisenhower Drive North
Goshen, Indiana 46526
USA

Tel: (+1) 574-534-2585
Fax: (+1) 574-534-3417

E-Mail: saleshad@stellite.com